

TECHNICAL SPECIFICATIONS
QUALITY LABORATORY
MODEL
23X180 MUMBLE-G/23X180
BODY TYPE
PORCELAIN GROUP Bla

| Body Technical Specifications | | Test Method | Standard Value | Pass/Fail |
|-------------------------------------------------------------------------------------------------------------------------|--|--------------|----------------|-----------|
|  Length and width | | ISO 10545-2 | ± 0.6 % | Yes |
| | | | ± 5 % | Yes |
| | | | ± 0.5 % | Yes |
| | | | ± 0.5 % | Yes |
| | | | ± 0.5 % | |
|  Water absorption | | ISO 10545-3 | <0.5 % | Yes |
|  Breaking strength | | ISO 10545-4 | >1300 N | Yes |
| | | | >35 N/mm² | Yes |
|  Frost resistance | | ISO 10545-12 | RESIST | Yes |
|  Linear thermal expansion coefficient | | ISO 10545-8 | 9*10^-6 K^-1 | Yes |

| Surface Technical Specifications | | Test Method | Standard Value | Pass/Fail |
|----------------------------------------------------------------------------------------------------------------------|--|---------------|----------------|-----------|
|  Slipperiness | | DIN-51130 | R9 | Yes |
| | | UNE-ENV-12633 | CLASS 1 | Yes |
|  Surface abrasion resistance (PEI) | | ISO 10545-7 | 4 | Yes |
|  Deep abrasion resistance | | ISO 10545-6 | - | - |
|  Surface hardness (MOHS scale) | | EN-101 | 5 | Yes |
|  Acids and alkalis resistance | | ISO 10545-13 | GLA/GLA | Yes |
|  Crazing resistance | | ISO 10545-11 | RESIST | Yes |
|  Staining resistance | | ISO 10545-14 | 5 | Yes |
|  Surface Quality | | ISO 10545-2 | > 95 % | Yes |

GOODS ARE IN CONFORMITY WITH ISO 13006 STANDARDS